## Industriegewebe // Industrial Mesh

## TECHNISCHE DATEN // LCP - POLYARYLAT GEWEBE







Material	Gewebecode	Maschen- weite	Offene Fläche	Fadenanzahl Kette / Schuss	Fadenanzahl Kette / Schuss	Faden- durchmesser	Gewebe- dicke	Einsatztemperatur trocken
material	mesh code			thread count warp / weft	thread count warp / weft	thread diameter	mesh thickness	working temperature dry
LCP		μm	%	cm	inch	μm	μm	°C
LCP	0040/45PW	40	45	165	420	20	28	280
LCP	0043/41PW	43	41	150	380	24	33	280
LCP	0047/49PW	47	49	150	380	20	28	280
LCP	0053/47PW	53	47	130	330	24	33	280
LCP	0145/74PW	145	74	59	150	24	42 / cal. 34	280

Die technische Daten beziehen sich auf durchschnittlichen Werte, die bei Produktionsmustern festgestellt wurden, mit Ausnahme von Fadendurchmesser, wofür der Nominalwert ausgedrückt wird. Durch die Kontrolle und Verbesserung unserer Produkte behalten wir uns die Änderung der technischen Daten jederzeit vor.

> The listed technical specifications, exception made for the thread diameter indicated with its nominal value, are referred  $to the \it arithmetic \it mean \it value \it of \it production \it samples \it and \it are \it subject \it to \it change, in \it accordance \it of \it improving \it our \it products.$

Flüssigkristallpolymer - Polyarylat Liquid Crystal Polymer - Polyarylate