Industriegewebe // Industrial Mesh

TECHNISCHE DATEN // **PEEK - POLYETHERETHERKETON** GEWEBE

TECHNICAL DATA // **PEEK - POLYETHERETHERKETON** MESH

PVF MESH & SCREEN TECHNOLOGY

Material	Gewebecode	Maschen-weite	Offene Fläche	Faden-durchmesser	Gewebe-dicke	Einsatztemperatur trocken
material	mesh code	mesh opening	open area	thread diameter	mesh thickness	working temperature dry
PEEK		**µm**	**%**	**µm**	**µm**	**°C**
PEEK	0019/14PW	19	14	35	65	250
PEEK	0036/24PW	36	24	35	62	250
PEEK	0105/55PW	105	55	35	65	250
PEEK	0190/60PW	190	60	31	56	250
PEEK	0195/75PW	195	75	35	65	250
PEEK	0220/60PW	220	60	60	105	250
PEEK	0740/50PW	740	50	300	600	250
PEEK	1025/45PW	1025	45	500	1040	250

Die technischen Daten beziehen sich auf durchschnittliche Werte, die bei Produktionsmustern festgestellt wurden, mit Ausnahme vom Fadendurchmesser, wofür der Nominalwert ausgedrückt wird.
Durch die Kontrolle und Verbesserung unserer Produkte behalten wir uns die Änderung der technischen Daten jederzeit vor.
The listed technical specifications, exception made for the thread diameter indicated with its nominal value, are referred to the arithmetic mean value of production samples and are subject to change, in accordance of improving our products.

PEEK
Thermoplastisches Halbkristall - Polymer
Thermoplastic semi-crystalline polymer

PVF Mesh & Screen Technology GmbH | Adalbert-Stifter-Weg 30 | 85570 Markt Schwaben | **T** +49 8121 4784-0 | **E** info@pvfgmbh.de | **I** www.pvfgmbh.de |